

PLASPERTEX PAINT CO LTD

Technical Product Data sheet

01.12

Product Name	S/B Stabiliser
Product reference	PP22
Product description	S/B Stabiliser is a solvent borne clear masonry binding primer based on acrylic resins. Improves adhesion of finishing coatings to friable, chalking masonry surfaces.
Uses	Primer/stabiliser for friable or chalky masonry surfaces
Pack sizes availability	5 & 25 litres
Colour range	Clear.
Specific gravity	Approx 0.8
Flash point	Flammable Flash point approx 40deg C
Recommended Spreading rate	Approx. 5 – 8 m ² /litre depending on surface porosity Ensure all applied material is absorbed into the surface
Solids content	Approx 13% w/w
Drying time	Approx 2 - 4 hours 20°C 65%RH depending on depth of penetration.
Over-coating time	Approx 12 hours 20°C 65%RH
Minimum application temperature	The performance of S/B Stabiliser is not adversely affected by low temperatures. However, do not apply during frosty or foggy weather or onto wet surfaces
Recommended dry film thickness	N/A
Method of application	Ideally apply by brush working well into the surface. May be low pressure sprayed if required
Preparation	Surfaces must be clean, sound and dry and prepared in accordance with BS6150 Painting of buildings – code of practice. Treat organic growth with fungicidal solution. Remove any unsound previous coating and weak material and repair with suitable exterior repair products before coating with S/B Stabiliser.
Storage life	Min 12 months in original sealed containers. Protect from frost and direct heat
Thinning/cleaning	Do not thin. Wash equipment immediately after use with D40 solvent or white spirit.
Safety precautions	Refer to the safety data sheet before use
Volatile organic content (voc)	Limit for this product Cat A/h 750g/l (2010). This product contains maximum 700g/l VOC
Disposal	<p>When this coating, in its liquid state, as supplied or skinned, becomes a waste, it is categorised as hazardous waste, with code 08 01 11 (list of hazardous wastes)</p> <p>Used containers, drained and/or rigorously scraped out and containing dried residues of the supplied coating, are categorised as non-hazardous waste, with code 15 01 04 (list of wastes)</p> <p>If mixed with other wastes the above waste codes may not be applicable</p>

